



| <b>Coated Panels - 100 PSI</b> |             | <b>Cleaning Rate</b>      | <b>Application Rate</b>    | <b>Speed</b>             | <b>Usage</b>   | <b>Blasting 1000'</b> |                   |            |
|--------------------------------|-------------|---------------------------|----------------------------|--------------------------|----------------|-----------------------|-------------------|------------|
| <b>Abrasive</b>                | <b>Size</b> | <b>Ft<sup>2</sup>/min</b> | <b>Lbs./Ft<sup>2</sup></b> | <b>Ft<sup>2</sup>/Hr</b> | <b>Lbs./Hr</b> | <b>Lbs./Min</b>       | <b>Time (Hrs)</b> | <b>Lbs</b> |
| TRU                            | Med-Coarse  | 2.47                      | 1.6                        | 148.2                    | 237.1          | 3.95                  | 6.75              | 1,600      |
| Garnet                         | 30x60       | 2.00                      | 2.7                        | 120.0                    | 324.0          | 5.40                  | 8.33              | 2,700      |

| <b>Coated Panels - 90 PSI</b> |             | <b>Cleaning Rate</b>      | <b>Application Rate</b>    | <b>Speed</b>             | <b>Usage</b>   | <b>Blasting 1000'</b> |                   |            |
|-------------------------------|-------------|---------------------------|----------------------------|--------------------------|----------------|-----------------------|-------------------|------------|
| <b>Abrasive</b>               | <b>Size</b> | <b>Ft<sup>2</sup>/min</b> | <b>Lbs./Ft<sup>2</sup></b> | <b>Ft<sup>2</sup>/Hr</b> | <b>Lbs./Hr</b> | <b>Lbs./Min</b>       | <b>Time (Hrs)</b> | <b>Lbs</b> |
| TRU                           | Med-Coarse  | 1.86                      | 2.1                        | 111.6                    | 234.4          | 3.91                  | 8.96              | 2,100      |
| Garnet                        | 30x60       | 1.78                      | 2.6                        | 106.8                    | 277.7          | 4.63                  | 9.36              | 2,600      |

| <b>CR STEEL - 100 PSI</b> |             | <b>Cleaning Rate</b>      | <b>Application Rate</b>    | <b>Speed</b>             | <b>Usage</b>   | <b>Blasting 1000'</b> |                   |            |
|---------------------------|-------------|---------------------------|----------------------------|--------------------------|----------------|-----------------------|-------------------|------------|
| <b>Abrasive</b>           | <b>Size</b> | <b>Ft<sup>2</sup>/min</b> | <b>Lbs./Ft<sup>2</sup></b> | <b>Ft<sup>2</sup>/Hr</b> | <b>Lbs./Hr</b> | <b>Lbs./Min</b>       | <b>Time (Hrs)</b> | <b>Lbs</b> |
| TRU                       | Med-Coarse  | 4.00                      | 1.60                       | 240.0                    | 384.0          | 6.40                  | 4.17              | 1,600      |
| Garnet                    | 30x60       | 3.74                      | 2.70                       | 224.4                    | 605.9          | 10.10                 | 4.46              | 2,700      |

| <b>CR STEEL - 90 PSI</b> |             | <b>Cleaning Rate</b>      | <b>Application Rate</b>    | <b>Speed</b>             | <b>Usage</b>   | <b>Blasting 1000'</b> |                   |            |
|--------------------------|-------------|---------------------------|----------------------------|--------------------------|----------------|-----------------------|-------------------|------------|
| <b>Abrasive</b>          | <b>Size</b> | <b>Ft<sup>2</sup>/min</b> | <b>Lbs./Ft<sup>2</sup></b> | <b>Ft<sup>2</sup>/Hr</b> | <b>Lbs./Hr</b> | <b>Lbs./Min</b>       | <b>Time (Hrs)</b> | <b>Lbs</b> |
| TRU                      | Med-Coarse  | 3.28                      | 2.0                        | 196.8                    | 393.6          | 6.56                  | 5.08              | 2,000      |
| TRU                      | Coarse      | 3.88                      | 2.6                        | 232.8                    | 605.3          | 10.09                 | 4.30              | 2,600      |

|        |       |      |     |       |       |      |      |       |
|--------|-------|------|-----|-------|-------|------|------|-------|
| Garnet | 30x60 | 3.54 | 2.6 | 212.4 | 552.2 | 9.20 | 4.71 | 2,600 |
|--------|-------|------|-----|-------|-------|------|------|-------|